Fire Zero Liquid

Fire-resistant paint for sealing the USB Fire Zero membrane
Riwega | eternitycomfort

Technical data sheet
of: 12/09/2018
Art. 02010342
Rev.02 of: 19/08/2021

Properties	
Composition	Graphite-based water paint
Content	5 kg (20 kg can on request)
Volume mass	1,22 (±0,02) kg/l
Dry residue	71 (± 2 %) by weight
Viscosity	27000 (±3000) cps (RVT 20 rpm, impeller 5 a 23°C)
Binder	Emulsion of fine resins in the aqueous phase
Film appearance	Opaque
Colour	Anthracite
Application temperature	+10°C / +35°C
Coverage	Approx.1,2 -1,4 kg/m^2 (approx.5,6 kg per roll of USB Fire Zero)
Drying time (20°C) "dust free"	Approx.1 hour (dry to the touch after approx.3 hours)
Drying time (20°C) "in depth"	Approx.24 -36 hours (depends on the thickness of the layer)
Drying time (20°C) "complete"	Approx.4-5 days
Overpaintable	Yes (after approx.6-8 hours)
Packaging	1 can
Storage	Store in the original packaging, in a dry place with a temperature between + 8 ° C and + 30 ° C, for max. 12 months
Installation warnings	Do not apply on too hot surfaces, causing adhesion problems of the product to the substrate, drying too fast with cracks or surface defects due to an abnormal film formation. Do not apply in high environmental humidity conditions and in case of rain. Do not apply on wet surfaces. Apply on clean, dust and grease-free surfaces. Not afraid of frost. Mix well before use. Do not dilute.

Riwega S.r.l. reserves the possibility to review or change this document. The updated document can be found on the website www.riwega.com. This document replaces the previous version.