USB Micro 230/20

Vapour control layer

Riwega | eternitycomfort

Rev.09

Technical data sheet
of 05/03/2015
Art. 02030230
of 19/02/2024

Material	PP.PP.PP	ÉMISSIONS DANS L'AIR INTÉRIEUR A+	CE EN 13984
Film	PP		
Colour	Dark blue		
Roll width	1,5 m		
Roll length	50 m		
Roll weight	17 Kg	g BB Ausschuss zur gesundheitlichen Bewertung von Bauprodukten	15 years guarantee
Classification in accordance with UNI 11470 (IT)	A		
Classification in accordance with Önorm B4119/B3661 (A	Typ I		
Classification in accorance with SIA 232-1 (CH)	VO		
Conforms to DTU (FR)	31.2		
Available in TOP SK version	02020126		

PROPERTIES	METHOD	UNITS	NOMINAL VALUE
Areal mass	EN 1849-2	g/m^2	220 (±10g/m2)
Air layer equivalent to the vapour passage [Sd]	EN ISO 12572	m	20
Water vapour diffusion [DVA]	EN ISO 12572	g/m^2 / 24h	ca. 1,5
Water column	EN 20811	cm	> 900
Resistance to water penetration	EN 13984 (EN1928 Met.A)	-	Passed
Tensile strength MD*	EN 12311-1	N/50mm	400 (±30N/50mm)
Tensile strength CD*	EN 12311-1	N/50mm	280 (±30N/50mm)
Elongation MD*	EN 12311-1	%	60 (±15%)
Elongation CD*	EN 12311-1	%	70 (±15%)
Resistance to tearing MD*	EN 12310-1	N	250 (±15N)
Resistance to tearing CD*	EN 12310-1	N	320 (±15N)
Fire reaction	EN 13501-1	Class	E
UV-stability	-	Months	4
Temperature resistance	-	°C	-40 / +100
Durability			
Artificial ageing	EN 1926	-	Passed
Alkali resistance	EN 13984 (EN1928 Met.A)	-	Passed

Density	EN 1849-1	Kg/m^3	208
Thickness	EN 1849-2	mm	1,06
Vapour resistance coefficient [μ]	EN ISO 12572	-	18868
Vapour permeability coefficient	-	Kg/m*s*Pa	0,0102*10-12
Thermal conductivity [λ]	-	W/mK	0,22
Specific heat	-	J/KgK	1700

* MD= Machine Direction; CD= Cross Direction.

Riwega S.r.l. reserves the possibility to review or change these technical values. The updated technical data sheet can be found on the website www.riwega.com. This data sheet replaces the previous copy.