Tape Fire B 75

High-adhesion acrylic adhesive tape with fire reaction class B-s1,d0
Riwega | eternitycomfort

Technical data sheet
of: 29/05/2025
Art. 02040184
Rev.00 of: -

Article	02040184	-	-
Measurements	75 mm x 25 m	100 mm x 25 m	150 mm x 25 m
Colour	Nero		
Adhesive	Colla acrilica		
Adhesive backing	Fibra di vetro (E-glass)		
Mass per unit area	340 g/m^2		
Covering material	Silicone paper		
Thickness (without liner)	0,34 mm		
S_d-value	0,14 m		
Application temperature	+5°C (lower temperatures not yet tested)		
Operating temperature	-30°C / +90°C		
Resistance to detachment (after 72 hours)	20N/50mm - cohesive failure		
Tensile strength L/T*	4200N/50mm / 3100N/50mm (EN 12311-1)		
Tear resistance L/T*	290N / 390N (EN 12310-1)		
Elongation L/T*	6% / 5% (EN 12311-1)		
Fire reaction (EN 13501-1)	B-s1,d0**		
Packaging	16 rolls	12 rolls	8 rolls
Storage	Store the rolls in their original packaging, in a dry place away from UV rays at a temperature between +5°C and +40°C and relative humidity between 50% and 60%.		

*L = Longitudinal; T = Transversal

** Fire reaction class A2-s1,d0 (according to EN 13501-1) achieved in the system with Windtop UV Fire A2 50/225 or Panther Universal A2 50/225 membrane, with a maximum quantity of Tape Fire B 75 equal to 10% of the total surface area of the system.

Riwega S.r.l. reserves the possibility to review or change this document. The updated document can be found on the website www.riwega.com. This document replaces the previous version.